

## Amendments to the CLAIMS

This Listing of Claims will replace all prior versions and listings of claims in this application.

### Listing of Claims:

1. (Currently Amended) An interlayer film for a laminated glass, which contains a matrix resin, a liquid plasticizer, acetyl acetone, alkali metal and at least one kind of metal selected from the group consisting of ~~magnesium~~ and alkaline earth metal, the content of the alkali metal being 20 to 120 ppm, the content of the at least one kind of metal selected from the group consisting of ~~magnesium~~ and alkaline earth metal being 15 ppm or more and less than 60 ppm, and the content of the acetyl acetone being 0.008 to 0.1 parts by weight ~~or more~~ with respect to 100 parts by weight of the matrix resin.
2. (Currently Amended) The interlayer film for a laminated glass according to claim 1, wherein the at least one kind of metal selected from the group consisting of ~~magnesium~~ and alkaline earth metal is magnesium.
- 3-4 (Canceled)
5. (Previously presented) An interlayer film for a laminated glass, according to claim 1, wherein magnesium is added as magnesium hexanoate, magnesium heptanoate, magnesium octanoate, or magnesium nonanoate.
6. (Previously presented) The interlayer film for a laminated glass according to claim 1, wherein the alkali metal is added as potassium

hexanoate, potassium heptanoate, potassium octanoate, or potassium nonanoate.

7. (Previously presented) A laminated glass, which has the interlayer film for a laminated glass according to claim 1 and two glass plates supporting the interlayer film for a laminated glass by sandwiching, and has a metal coating layer in at least one interface of two interfaces between the interlayer film for a laminated glass and the glass plates.

8. (Previously presented) A laminated glass, which has the interlayer film for a laminated glass according to claim 2 and two glass plates supporting the interlayer film for a laminated glass by sandwiching, and has a metal coating layer in at least one interface of two interfaces between the interlayer film for a laminated glass and the glass plates.

9. (Previously presented) A laminated glass, which has the interlayer film for a laminated glass according to claim 5 and two glass plates supporting the interlayer film for a laminated glass by sandwiching, and has a metal coating layer in at least one interface of two interfaces between the interlayer film for a laminated glass and the glass plates.

10. (Previously presented) A laminated glass, which has the interlayer film for a laminated glass according to claim 6, and two glass plates supporting the interlayer film for a laminated glass by sandwiching, and has a metal coating layer in at least one interface of two interfaces between the interlayer film for a laminated glass and the glass plates.

11. (New) The interlayer film for a laminated glass according to claim 1, wherein the maximum amount of acetyl acetone is 0.06 parts by weight.

12. (New) The interlayer film for a laminated glass according to claim 1, wherein the maximum amount of acetyl acetone is 0.012 parts by weight.